



Brand Name	<b>CENTANIN® 1)</b>				
Material Code					
Abbreviation	<b>CuMn27Ni</b>				
Chemical Composition (mass components) in %. Average values of alloy components					
<b>Cu</b>	<b>Ni</b>	<b>Mn</b>	<b>Al</b>		
67	5	27	1		

### Features and Application Notes

CENTANIN® is in the best tradition of Isabellenhütte's precision resistance alloys ZERANIN® 30, MANGANIN®, NOVENTIN® and ISAOHM®. CENTANIN® is especially characterized by a high resistivity and a low temperature coefficient of resistance between +20°C and +60 °C with a parabolic behavior of the R(T) curve. CENTANIN® is excellently suitable for the production of standard resistors with a maximum working temperature in air of +140°C. It is also suitable for heating elements with low conductor temperatures up to 300°C in non-oxidizing atmosphere. Due to its low melting point, CENTANIN® is also proved successfully for years in thermal spraying applications, e.g. heating layers and heated surfaces.

### Form of Delivery

CENTANIN® is supplied in the form of round wires in the range of 1 to 6 mm Ø in bare annealed condition. Also available on request other Diameters, sheets, ribbons, flat wires, stranded wires and rods.

### Notes on Treatment

This alloy is in hard drawn condition subject to stress-corrosion-cracking and should be annealed immediately after being processed.

### Electrical Resistance in Annealed Condition

Temperature coefficient of electrical resistance between +20 °C and +60 °C 10 <sup>-6</sup> /K	Electrical resistivity in Ωxmm <sup>2</sup> /m at Reference Values					
	Nom. value	+20 °C Perm. value [%]	+100 °C	+300 °C	+400 °C	+500 °C
					Reference values	
<b>±20</b>	<b>1.00</b>	<b>+10</b>	<b>1.00</b>	-	-	-

### Physical Characteristics (Reference Values)

Density at +20 °C	Melting point	Specific heat at +20 °C	Thermal conductivity at +20 °C	Average linear thermal expansion coefficient between +20 °C and		Thermal EMF against copper at
g/cm <sup>3</sup>	°C	J/g K	W/m K	+100 °C	+400 °C	+20 °C
<b>7.8</b>	<b>+900</b>	<b>0.42</b>	-	<b>20</b>	-	<b>≤+3</b>

### Strength Properties at +20 °C in Annealed Condition

Tensile Strength N/mm <sup>2</sup>	Elongation (L <sub>0</sub> = 100 mm) % at nominal diameter in mm
<b>[Min.]</b>	Over 1 min.
<b>540</b>	<b>25</b>

1) CENTANIN® is a registered trademark of Isabellenhütte Heusler GmbH & Co. KG.

**Precision resistance alloys:**

	ZERANIN®30	MANGANIN®	ISOTAN®	ISABELLIN® A	NOVENTIN®	CENTANIN®	ISAOHM®
resistivity [ $\mu\Omega \cdot \text{cm}$ ]	29	43	49	50	90	100	132
low TCR	●	●	●	◐	●	◐	●
low thermal EMF	◐	●	○	○	●	○	○
solderability / workability	●	●	●	◐	●	◐	○

very good ●  
 good ◐  
 less good ○